

Satin Acqua Water-Borne Premium Enamel

This is a product of excellent quality and glossiness. It is water-borne, offering low odor and dispensing with the use of turpentine. It has high resistance to weathering, is easy to apply and clean, with an excellent spread, adherence and coverage, excellent finish and performance.

This is a quick-drying product, with excellent resistance to fungi and does not become yellow with the action of the weather.

This product complies with ABNT NBR 11702 type 4.2.3.2

USE RECOMMENDATIONS

Indicated for painting external and internal surfaces of wood, ferrous metals, galvanized steel, aluminum and PVC.

BASIC PROPERTIES

Colors	White plus 1800 in the Watercolor System
Finish	Satin
Solids per Mass	43% \pm 2
Solids per Volume	35% \pm 2
VOC	32.0 g/L
Specific Weight at 25°C	1.23 g/cm ³ (approximate value)
pH	8.8 - 9.5
Flash Point	Not applicable
Storage time	24 months
Toxicity	Consult MSDS
Type of packaging	0.9L and 3.6L

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

APPLICATION DATA

Recommended number of coats	2 to 3 coats
Thickness per coat:	Wet film thickness – 80 to 110 µm Dry film thickness – 30 to 45 µm
Theoretical spreading rate:	Up to 6.25 m ² finished/900 mL Up to 25 m ² finished/3.6 L Comments: For products from the Watercolors Tintometric System, consider the proportional spreading rate of up to 6.94 m ² /L. May vary depending on surface conditions. For roller and brush, dilute 10% – 15% with drinking water.
Dilution:	For spray gun, dilute 20% - 30% with potable water.

DRYING

Temperature	25°C
To touch	30 to 40 minutes
Handling/Repainting	4 hours
Final	5 hours

Considerations: Do not paint on rainy days, at temperatures below 10°C or above 35°C or humidity above 80%. The painted surface can only be washed (cleaned) 30 days after its application. The painted surface should be cleaned with water and neutral detergent, soft sponge or cloth. Cleaning should be gentle and all over the painted surface to avoid staining or paint removal issues. Do not clean with a dry cloth, as the surface may be polished. Fading may occur in some colors, depending on the combination of pigments used, however, this will not cause any problems with the integrity of the paint film.

SURFACE PREPARATION - ABNT NBR 13.245 Standard

The surface must be dry, firm and dust free, free of contaminants such as: oils, salts, grease, fat, dust, etc., duly applied with the recommended primer.

Loose or poorly adhered parts must be scraped and/or brushed.

On aged paint, sand superficially, leaving the surface free from shine and removing loose particles.

Before starting painting, observe the following instructions:

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

TYPE OF SURFACE		TREATMENT
Wood	New	Sand wood splinters. Apply one coat of the diluted Anjo Leveling White Primer 10-15% with Anjo White Spirit.
	Repainting	Eliminate glossiness before application.
Iron	New with hint of rust	Sand and apply a coat of Anjo Orange Primer (red oxide).
	With rust	Completely remove rust with sandpaper and/or wire brush. Apply a coat of Anjo Red Oxide Primer.
	Repainting	Sand and completely eliminate glossiness. Treat rust spots as instructed above.
Aluminum / Galvanized Steel / PVC	New	No primer application is required.
	Repainting	Scrape and sand to eliminate glossiness and remove old, poorly adhered paint.
Zinc plated	New	Apply Anjo Primer for Galvanized Surfaces
	Repainting	Scrape and sand to eliminate glossiness and remove old, poorly adhered paint.

APPLICATION METHOD

Brush – Touch-ups and other finishes where the roller cannot reach.

Sheepskin roller – low pile (needs additional coats to achieve desired thickness)

Anti-drop synthetic wool roll – 10 mm.

DeVilbiss conventional spray gun - 502 EX 67 or similar.

Pressure in the tank: 0.5 – 1.5 kgf.

Spray pressure: 2.5 - 3.5 kgf/cm² (35 to 50 psi).

APPLICATION INSTRUCTIONS

Before starting any painting, always pay attention to the following procedure:

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

Sand: sand the surface, removing loose parts and promoting greater adhesion to the product that will be subsequently applied.

Cleaning: clean with a cloth or broom to remove dust from the surface and ensure adherence of the product that will be applied to the surface.

Seal: the use of primers evens out surface absorption, in addition to significantly improving the spreading rate of the product to be applied.

Homogenize: Homogenization is required for the complete mixing of all components, as well as the dispersion of pigments. As the product will be kept in stock, this operation is indispensable for the characteristics to remain unchanged.

Dilute: dilution must observe the recommended instructions, so that the product can offer excellent performance such as coverage, spreading rate, leveling and application.

Apply: always pay attention to loose or badly adhered parts of the substrate, in these cases, the surface preparation recommendations must be observed.

In the case of cuts, always make the cut first with a brush and then apply with a roller. Application with a roller must be carried out following the procedure: apply in an M shape, turning the application in W direction.

RECOMMENDED PRIMER

Red Oxide Primer

White Leveling Primer

For others, consult our Technical Department

SAFETY RECOMMENDATION

- Store the product in closed, ventilated environments with maximum temperatures of 40°C.
- When applied, the product emits vapors that must be avoided with the correct use of PPE, such as masks and respirators, ensuring proper ventilation during application.
- Avoid skin contact using gloves, goggles, suitable garments, protective creams, etc.
- Keep away from children and animals.

COMMENTS

In order to provide and ensure the quality of the products, it is essential to use our complete Anjo painting system (bases, putties, thinners and finishes) observing the instructions contained on the packaging or in the technical report.

Do not store the diluted product. Do not use different batches to continue painting, there may be a change in tone, as well as in the finish.

This information represents the best of our knowledge when this document was published. We remind you that optimal final results when applying the products depend on factors that exceed our control and that concern the surface preparation and the technical knowledge of the applicator. The company reserves the right to change these specifications without prior notice.

The spreading rate of this product will vary according to the type of surface and the painting system to be used, the thickness applied, method and application technique, the type and roughness of the substrate and environmental conditions, etc.

Usually an excellent result may be achieved with 2 or 3 coats, but, depending on the type of color or condition of the wall, more coats may be needed.

The values found for the specific weight and drying tests (with the specified thickness) were obtained in the laboratory at a temperature of 25°C. With temperatures other than those mentioned, the values established above tend to be different from those specified.

The instructions contained in these specifications are based on our experience and technical knowledge; however, some factors are beyond our control as a manufacturer, such as: surface preparation, application, working conditions, etc.

The use of solvents other than those specified without prior approval from Anjo may affect product performance and void product warranty.

We take no responsibility for material and personal damage caused by the misuse of the information contained in these specifications and of the products mentioned.

These specifications are subject to change without prior notice.